•TRUSTED QUALITY SINCE 1921•
RUST-OLEUM®
SPECIALTY

# RUST-OLEUM®
# POWER & EQUIPMENT SPRAYS

## DESCRIPTION AND USES

Rust-Oleum® Power and Equipment is a durable, rust preventive enamel for touch ups or complete refinish jobs. Stops Rust® formula offers excellent coverage, chip resistance and color retention. Ideal for lawn mowers, snow blowers, grounds maintenance equipment, construction vehicles, hand tools and more.

Not for use on engine components that exceed 200°F. Not for use on galvanized metal. Not for use on rubber.

**NOTE -** Rust-Oleum® Plastic Primer or Universal Bonding Primer is highly recommended for plastic components.

## PRODUCTS

| SKU | DESCRIPTION (Aerosol) |
|---|---|
| 350444 | Gloss Toolbox Red |
| 395420 | Gloss Rugged Red |
| 395421 | Gloss Outdoor Yellow |

## PRODUCT APPLICATION

### SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to thoroughly dry.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated coatings. Use 7769 Rusty Metal Primer for sound rusted or clean metal before application of a finish coat. 7780 Clean Metal Primer is best for clean metal but may be used on sound rusted metal as well.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

## PRODUCT APPLICATION (cont.)

### APPLICATION

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85% to ensure proper drying. Protect the surrounding area from overspray. Overspray can carry a significant distance. Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Hold can upright 10-16" from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

### DRY & RECOAT

Dry and recoat times are based on 70ºF (21°C) and 50% relative humidity. Dries to the touch in 2-4 hours and can be handled in 5-9 hours. Recoat within 1 hour or after 48 hours.

### CLEAN-UP

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



Form: RAK-92
Rev.: 030326

• TRUSTED QUALITY SINCE 1921 •
RUST-OLEUM® SPECIALTY

# RUST-OLEUM®
# POWER & EQUIPMENT SPRAYS

## PHYSICAL PROPERTIES

| | | POWER & EQUIPMENT SPRAYS |
|---|---|---|
| **Resin Type** | | Oil Modified Alkyd |
| **Pigment Type** | | Varies with color |
| **MIR** | | 0.95 Max |
| **Fill Weight** | | 12 ounces |
| **Practical Coverage (assumes 15% material loss)** | | Approximately 6-7 sq.ft./can (0.54-0.63 $m^2$/can |
| **Dry Times at 70-80ºF (21-27ºC) and 50% Relative Humidity** | **Touch** | 2-4 hours |
| | **Handle** | 5-9 hours |
| | **Recoat** | Within 1 hour or after 48 hours |
| **Dry Heat Resistance** | | 200°F (93°C) |
| **Shelf Life** | | 5 years |
| **Flash Point** | | -156°F (-104°C) |
| **Safety Information** | | For additional information, see SDS |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.